



PERFORMANCE SPECIFICATION

SC150BN



The North American Green SC150BN erosion control blanket is constructed of 100% biodegradable materials with a 70% agricultural straw and 30% coconut fiber blend matrix and has a functional longevity of approximately 18 months. (NOTE: functional longevity may vary depending upon climatic conditions, soil, geographic location, and elevation). The straw and coconut fibers shall be evenly distributed over the entire area of the mat. The blanket shall be covered on the top and bottom with 100% biodegradable natural organic fiber netting woven into an approximate 0.50 inch x 1 inch (1.27 x 2.54 cm) mesh. The blanket shall be sewn together with biodegradable thread on 1.50 inch (3.81 cm) centers. The following list contains further physical properties of the SC150BN erosion control blanket.

<u>Property</u>	<u>Test Method</u>	<u>Typical</u>
Thickness	ASTM D5199/ECTC	0.29 in (7.47 mm)
Resiliency	ECTC Guidelines	86 %
Mass per Unit Area	ASTM D6475	9.66 oz/yd ² (328 g/m ²)
Water Absorption	ASTM D1117/ECTC	158 %
Swell	ECTC Guidelines	46 %
Stiffness/Flexibility	ASTM D1388/ECTC	0.42 oz-in (4,737 mg-cm)
Light Penetration	ECTC Guidelines	11.70 %
Smolder Resistance	ECTC Guidelines	Yes**
MD Tensile Strength	ASTM D5035	280.80 lbs/ft (4.10 kN/m)
MD Elongation	ASTM D5035	9.50%
TD Tensile Strength	ASTM D5035	205.20 lbs/ft (2.99 kN/m)
TD Elongation	ASTM D5035	13.20 %

**Material is smolder resistant according to specified test

MD - Machine direction

TD - Transverse direction

Slope Design Data

Channel Design Data

Bench Scale Testing†

Cover Factors (C)				Channel Roughness Coefficients	
Slope Length (L)	Slope Gradient (S)			Flow Depth	Manning's 'n'
	≤ 3:1	3:1 - 2:1	≥ 2:1		
≤ 20 ft (6 m)	0.00009	0.029	0.063	≤ 0.50 ft (0.15 m)	0.050
20 - 50	0.005	0.055	0.092	0.50-2.00 ft	0.050-0.018
≥ 50 ft (15.2 m)	0.010	0.080	0.120	≥ 2.00 ft (0.60 m)	0.018
				Max. Permissible Shear Stress 2.10 lbs/ft ² (100.0 Pa)	

Unvegetated Channel	3.9 lbs/ft ²
---------------------	-------------------------

Approximate Max Flow Velocity	8.00 ft/s (2.44 m/s)
-------------------------------	----------------------

For most accurate design data consult ECMDS™

Manning's 'n' expressed in English units

†Bench Scale Testing

Bench scale tests are index property tests. These tests are not indicative of field performance and therefore should not be used in design to establish performance levels for rolled erosion control products. Bench scale tests are performed according to methods developed by the Erosion Control Technology Council (ECTC).