



Sales Office:
 Engineered Synthetic Products, Inc.
 Phone (770) 564-1857
 Fax (770) 564-1818
 www.espsynthetics.com

Geotextile Product Description Sheet

SKAPS M404

SKAPS woven geotextile fabrics are woven polypropylene materials offering optimum performance when used in stabilization and drainage applications. Produced from first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. SKAPS M404 resists ultraviolet resistance, rotting, biological degradation and it is chemically inert to any natural bases or acids Unless indicated below, all listed properties are Minimum Average Roll Values:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/sy (g/sm)	5.6 (190)
Grab Tensile	ASTM D 4632	lbs (kN)	300X200(1.33X0.889)
Grab Elongation	ASTM D 4632	%	24x10
Trapezoidal Tear	ASTM D 4533	lbs (kN)	65 (0.29)
Puncture Resistance	ASTM D 4833	lbs (kN)	100 (0.444)
Puncture Resistance	ASTM D 6241	lbs (kN)	500 (2.20)
Mullen Burst Strength	ASTM D 3786	psi (kPa)	450 (3100)
Water Flow*	ASTM D 4491	gpm/sf (l/min/sm)	35 (1376)
Permittivity*	ASTM D 4491	Sec ⁻¹	0.5
AOS*	ASTM D 4751	US Sieve (mm)	40 (0.425)
Percent Open Area	CW0-02215-86	%	4
UV Resistance		%/hrs	70/500

* At the time of manufacturing. Handling, storage and shipping may change these properties.

PACKAGING	
Roll Dimensions (W x L) – ft	12.5 x 300
Square Yards Per Roll	400
Estimated Roll Weight - lbs	155

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.

SKAPS Industries, 335 Athena Drive., Athens, GA 30601, Phone (706) 354-3700, Fax (706) 354-3737, Email: info@skaps.com